




# Secutex® GRK Classification



# Geo-Coastal Engineering Ltd

Tel: 01-9060333

Email: info@geo-coastal.ie

Website: www.geo-coastal.ie

## Technical Information

### Product description:

Needle punched non woven geotextiles for road works according to the geotextile robustness classes (GRK) taken from the leaflet AA 5.15

## Non-Woven Geotextile

Characteristic Value	Test Method (based on)	Unit	151-GRK 3 C	201-GRK 3 C	251-GRK 4 C	301-GRK 5 C	351-GRK 5	401-GRK 5
Raw materials			Polypropylene (PP), white					
Mass per unit area	EN ISO 9864	g/m <sup>2</sup>	150	200	250	300	335	400
Thickness	EN ISO 9863-1	mm	1	1.2	1.4	1.6	3	3.3
Tensile strength (longitudinal)	EN ISO 10319	kN/m	6.0	7.5	9.5	13.0	14.5	18.0
Tensile strength (transverse)	EN ISO 10319	kN/m	10.0	12.0	18.0	22.0	23.0	25.0
Elongation at max. strength (longitudinal)	EN ISO 10319	%	60	60	60	60	60	60
Elongation at max. strength (transverse)	EN ISO 10319	%	40	40	40	40	40	40
Puncture force (mean-standard deviation)	EN ISO 12236	N	1670	1750	2780	3890	4000	4000
Elongation at static puncture strength	EN ISO 12236	%	30	30	30	30	35	35
Characteristic opening size	EN ISO 12956	mm	0.15	0.12	0.09	0.09	0.08	0.08
Water permeability	EN ISO 11058	m/s	8.0 x 10 <sup>-2</sup>	6.0 x 10 <sup>-2</sup>	5.0 x 10 <sup>-2</sup>	4.0 x 10 <sup>-2</sup>	1.0 x 10 <sup>-3</sup>	1.0 x 10 <sup>-3</sup>
Flow rate <sub>H50</sub>	EN ISO 11058	l/sm <sup>2</sup>	80	60	50	40	1.0 x 10 <sup>-3</sup>	1.0 x 10 <sup>-3</sup>
** Trapezoidal tear strength long./trans.	ASTM-D-4533	N	150/250	200/300	300/450	400/600	450/650	500/700
** Grab tensile strength long./trans.	ASTM-D-4632	N	250/400	400/600	600/900	800/1200	900/1300	1000/1500
** Puncture force	ASTM-D-4533	N	350	450	600	750	800	800
Bonding method	-	-	needle-punched	needle-punched	needle-punched	needle-punched	needle-punched	needle-punched
Detector tested	-	-	yes	yes	yes	yes	yes	yes
Standard roll dimension	-	-	5.90 x 150	5.90 x 150	5.90 x 125	5.90 x 100	5.90 x 100	5.90 x 100

\*\* = for information only, not included in MQC

Please contact our office for information regarding geotextiles that are not covered in this chart.

The above technical values are average values over the roll width. These data are guiding values achieved in laboratories and independent testing institutes. Our products can be subject to change without prior notice.

